



The Chemical Company

PRODUCT DATA

7 07 16 00

Cementitious
Waterproofing

THOROSEAL®

Waterproof cement-based coating
for concrete and masonry

Description

Thoroseal® is a Portland-cement-based coating for concrete and masonry that resists both positive and negative hydrostatic pressure. Polymer-modified with Acryl 60®, Thoroseal® creates a low-maintenance and highly durable waterproof barrier.

Yield

225 ft²/50 lb (20.9 m²/22.7 kg) bag as a base coat at 1/16" (1.6 mm) dry-film thickness.

450 ft²/50 lb (41.8 m²/22.7 kg) bag as a topcoat at 1/32" (0.8 mm) dry-film thickness.

Coverage will vary depending on surface texture and porosity.

Packaging

THOROSEAL®

10 lb (4.5 kg) cans for Thoroseal® white and standard gray only

30 lb (13.6 kg) polyethylene-lined bags for Thoroseal® white and standard gray only

50 lb (22.7 kg) polyethylene-lined bags for Thoroseal® white, standard gray, all landscape colors and custom colors

60 lb (27.2 kg) pails for Thoroseal® white, standard gray, landscape colors, and custom colors

ACRYL 60®

1 quart (0.9 L) bottles

1 gallon (3.8 L) bottles

5 gallon (18.9 L) pails

30 gallon (113 L) drums

55 gallon (208 L) drums

Features

- Waterproof
- Resistant to both positive and negative hydrostatic pressure
- Breathable
- Compatible with high-performance coatings
- Aesthetically beneficial
- Aesthetically superior

Benefits

- Protects building interiors from dampness and moisture damage
- Suitable for use below grade interior and exterior and in water-treatment construction
- Allows interior moisture to escape without damaging coating
- Accepts a wide range of architectural coatings and textured finishes
- Hides minor surface defects and blemishes in architectural concrete
- Available in 10 landscape colors and in custom colors (with minimum order quantities)

Color

White and standard gray (this color is not uniform)

Custom and landscape colors are available for 5,000 lbs (2,268 kg) minimum order.

Ten landscape colors : bone, dijon, French vanilla, good earth, light khaki, Thoro® gray, Navajo white, parchment, pearl gray, and putty tan

Shelf Life

1 year when properly stored

Storage

Transport and store in unopened containers and keep in a clean, dry condition protected from rain, dew and humidity. Do not stack bags more than 2 pallets high.

If dry onsite storage of bags is unavailable or if project is located in a very wet, humid climate zone, then specify Thoroseal® packaged in 60 lb (27.2 kg) metal pails. Store Acryl 60® in similar conditions. Do not allow Acryl 60® to freeze.

Where to Use

APPLICATION

- Alternative to mechanical finishing or rubbing of concrete
- Waterproofing basement and retaining walls
- Foundations
- Bridges and tunnels
- Water cisterns

LOCATION

- Vertical and light-pedestrian horizontal surfaces
- Interior and exterior
- Above and below grade

SUBSTRATE

- Cast-in-place and precast concrete
- Block, brick and porous stone



Technical Data

Composition

Thoroseal® contains cement, graded sand, and proprietary additives.

Test Data

PROPERTY	RESULTS	TEST METHODS
Initial Set , min, at 70° F (21° C), 50% rh	10	Lab Method
Final Set , at 70° F (21° C), 50% rh	90	Lab Method
Density , (cured), lbs/ft ³ (kg/m ³)	129 (2,080)	Lab Method
Positive resistance to hydrostatic pressure , hrs, at 200 psi (1.4 MPa), 461 head ft, air cured at 70° F (21° C), 50% rh	752 No leakage, no softening	CRD C 48, modified
Negative resistance to hydrostatic pressure , hrs, at 200 psi (1.4 MPa), 461 head ft, air cured at 70° F (21° C), 50% rh	664 Limited dampness	CRD C 48, modified
Water absorption , %, boiling water submersion at 24 hours	3.6	ASTM C 67 (Section 7.3)
Compressive strength , psi (MPa) 7 days 28 days	4,200 (29) 6,030 (42)	ASTM C 109
Flexural strength , psi (MPa) 7 days 28 days	360 (2.5) 1,027 (7)	ASTM C 348
Tensile strength , psi (MPa) 7 days 28 days	250 (2) 440 (3)	ASTM C 190
Modulus of elasticity , psi (MPa) 28 days	2.72 x 10 ⁶ (1.87 x 10 ⁶)	ASTM C 469
Artificial weathering , hrs Xenon Arc Carbon Arc	5,000 = No failure 500 = No failure	ASTM G 26 ASTM G 23
Adhesion strength , psi (MPa)	418 (2.9)	Test by tensile bond
Artificial weathering ,	No cracking, loss of adhesion, checking, or other defect	Atlas Type DMC weatherometer
Freeze/thaw resistance , 200 cycles	No change	ASTM C 666 (Procedure B)
Salt spray resistance , 300 hours	No defect	ASTM B 117
Carbon Dioxide (CO₂) , in (mm)	1/16 (1.6) Equivalent to 3/4" (19 mm) new concrete	Lab Method Diffusion
Permeance , perms (metric permeability)	12 (0.10698) 18 x 10 ³ resistance	ASTM E 96 (water-vapor transmission) Swedish standard SS-02-15-82

Test Data, continued

PROPERTY	RESULTS	TEST METHODS
Wind-driven rain, hrs	8 = excellent	Fed. Spec. TT-P-0035 (Para 4.4.7)
Coefficient of thermal expansion, in/in/° F (mm/mm/° C), at 28 days	6.99×10^{-6} (5×10^{-7})	ASTM C 531
Impact strength (Gardener impact tester)	No chipping	Fed. Spec. TT-P-0035 (Cement paints para. 3.4.8)
Hardness, (Barber Coleman Impressor) Requirement min = 30, max = 60		Fed. Spec. TT-P-0035 (para 4.4.9)
7 days	35	
14 days	47	
21 days	52	
Abrasion resistance, 3,000 L sand	Passed	Fed. Spec. TT-P-141B
Reflectance		ASTM D 2244 using Hunterlab D-25 meter
Gray Thoroseal®	64.2	
White Thoroseal®	88.1	
Fungus resistance, at 21 days	No growth; meets all requirements	Fed. Spec. TT-P-29B
Surface burning characteristics		ASTM E 84
Flame Spread	0	
Smoke developed	5	
Fire Propagation	Index = 1.5	BS476: Part 6:1981
Flame spread	Class 1	BS476: Part 7:1971

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

How to Apply**Surface Preparation**

1. Surface preparation is extremely important for proper adhesion. Substrates must be sound and free of dust, dirt, laitance, paints, oils, grease, curing compounds or any other contaminants. Verify substrate has properly cured. Concrete should obtain 80% of design strength, typically achieved within 3 – 14 days. If efflorescence is present, mechanically remove it before proceeding. For extreme cases where this is not adequate, contact Technical Service.
2. Patch all holes and cracks before installation.
3. Relieve hydrostatic pressure in concrete block with weep holes.
4. Roughen or brush blast extremely smooth surfaces such as precast and cast-in-place concrete to ensure good mechanical adhesion of Thoroseal®.

Mixing

1. Mix Thoroseal® with a mixing liquid consisting of a blend of Acryl 60® diluted with water. Maximum dilution ratio is 1 part Acryl 60® to 3 parts water. Approximately 6 quarts of mixing liquid is needed per 50 lbs of Thoroseal® powder. Up to 2 additional quarts of mixing liquid may be added when using as a rubbing compound.
2. For best results, mechanically mix Thoroseal® with a slow-speed drill and mixing paddle. Gradually add the powder to the mixing liquid while drill is running.
3. When properly blended, Thoroseal® will have the lump-free consistency of smooth, heavy batter.
4. Allow the Thoroseal® and Acryl 60® mixture to rest undisturbed for a minimum of 10 minutes to fully wet out all the powder. Then remix the wet mixture and apply. A small amount of mixing liquid can be added to this remixing.
5. Pot life is 60 – 90 minutes at 70° F (21° C). At high temperatures and low relative humidity, pot life can be significantly less.

Application

1. Apply Thoroseal® with a Thoro® brush or broom or equivalent stiff fiber brush or by textured spray equipment. Spray applications of the first coat require back brushing or brooming to properly fill voids and achieve uniformity.
2. Completely dampen the substrate with water before application starts. Do not saturate the substrate, but keep it cool and damp throughout the application.
3. It is essential to work first coat thoroughly into the substrate to completely fill and cover all voids, holes and nonmoving cracks. Finish with a horizontal stroke for an even coat.
4. Allow to cure 24 hours, then apply the second coat and finish with a vertical stroke. Above grade, the second coat can be replaced with a Thoro® high-build architectural coating to achieve better color uniformity.
5. On block or masonry walls, allow 5 – 7 days before applying second coat to eliminate joint read through.

Specific Applications

Above-grade interior or exterior applications in positive pressure situations (direct contact with rain or standing water with a low head of pressure)

1. A 50 lb (22.7 kg) bag of Thoroseal® will provide the following coverage at the designated material usage.

Recommended coverage:

- First Coat: 2 lbs/yd² (1.1 kg/m²) = 225 ft²/50 lb bag (20.9 m²/22.7 kg bag)
- Second Coat: 1 lb/yd² (0.54 kg/m²) = 450 ft²/50 lb bag (41.8 m²/22.7 kg bag)
- Total: 3 lbs/yd² (1.6 kg/m²), cured nominal thickness of 1/16" (1.6 mm).

Coverage will vary depending on surface texture and porosity.

2. A 3 lbs/yd² (1.6 kg/m²) application rate does not eliminate surface irregularities such as struck mortar joints. To hide surface irregularities, spray and back-brush a base coat of Thoroseal® at 2 lbs/yd² (1.1 kg/m²) and allow it to cure for 5 – 7 days. Then spray apply and back trowel a topcoat of Thoroseal® Plaster Mix (see Form No. 1019908) at an application rate of 9 lbs/yd² (4.9 kg/m²).

BELOW-GRADE INTERIOR APPLICATIONS

1. The standard application is 3 lbs/yd² (1.6 kg/m²).

2. For high hydrostatic pressure conditions (over 15 psi [0.10 MPa]), increase application rate to 4 lbs/yd² (2.2 kg/m²) and waterproof from the positive side wherever possible.

BELOW-GRADE EXTERIOR APPLICATIONS

1. Use Thoroseal® Foundation Coating (see Form No. 1019907) For high hydrostatic pressure conditions (over 15 psi [0.10 MPa]), apply a base coat of Thoroseal® Foundation Coating at 2 lbs/yd² (1.1 kg/m²) and allow to cure for 5 – 7 days.

2. Then apply a topcoat of Thoroseal® Plaster Mix at 12 lbs/yd² (6.5 kg/m²). A steel trowel finish is recommended.

3. For both below-grade interior and below-grade exterior applications where water might move between vertical walls and slab or footer, it is recommended to cut out and place a Waterplug® cove at the wall and floor junction prior to the application of the Thoroseal® base coat.

4. Thoroseal® can be covered with extruded polystyrene insulation board during the second coat application. The board must be fully coated with Thoroseal® and embedded into the still-wet coating already in place on the walls. Exercise care when placing the coated board because it should not be moved or slipped. Once placed, do not move the board. After curing, prepare the above-grade portions of the boards by roughening or removing the surface skin and then coating with Thoroseal® to protect them from UV light degradation.

WATERPROOFING POTABLE WATER TANKS OR RESERVOIRS

1. Install Thoroseal® as directed in the general Application instructions.

2. After Thoroseal® has fully cured, wash down the Thoroseal® surface with saline solution (salt brine, 1 lb salt per 1 gallon water).

3. Leave saline solution on the entire Thoroseal® surface for at least 24 hours.

4. Rinse off saline solution completely. If needed, reapply saline solution until final rinse water is completely clean and clear.

Color Uniformity

With any cementitious product, such as Thoroseal®, it may be difficult to achieve color uniformity due to weather and substrate variability. For this reason, it may be necessary to apply a topcoat of a Thoro® architectural coating.

Clean Up

Promptly clean hands and all tools with warm water while product is still wet. Cured material may only be removed mechanically.

For Best Performance

- Thoroseal® must be modified with Acryl 60® to achieve the properties listed in the technical data section.
- Do not apply to substrates with active water leaks or moving cracks; patch all leaking static cracks and holes with Waterplug®. Repair any other nonmoving cracks or voids with the appropriate Thoro® repair product and repair all moving cracks or voids with appropriate sealant.
- Maintain or place expansion and control joints as necessary.

- Do not apply in rain or when rain is expected within 24 hours. Do not apply above 90° F (32° C) or below 40° F (4° C) or when temperatures are expected to fall below 40° F (4° C) within 24 hours. For hot and cold temperature applications, store Thoroseal®, Acryl 60® and water at 50° F (10° C) to 70° F (21° C) before use.
- Hot substrates will effect working time and material strength.
- Variations between inside and outside temperatures may result in condensation on below-grade walls treated with Thoroseal®. This can be alleviated by assuring that adequate ventilation exists.
- Windy, dry or hot conditions may require rewetting of Thoroseal® during cure and the use of polyethylene barriers.
- Before specifying Thoroseal® for water-retaining structures, conduct tests to determine water quality. Thoroseal® is not intended for continuous contact with acid or sulfate-containing water. Very soft water will have an adverse effect on Thoroseal®.
- Service temperatures: immersion, up to 140° F (60° C); cleaning water, up to 200° F (93° C); dry air, up to 220° F (104° C).
- On all projects, it is recommended that a sample be prepared on site and approved prior to the commencement of the work. The site sample should confirm the color, texture and workmanship required until the job is finished and accepted. Retain the sample until final approval is secured.
- Allow Thoroseal® to cure 7 – 10 days before immersion in water.
- Make certain the most current versions of product data sheet and MSDS are being used; call Customer Service (1-800-433-9517) to verify the most current version.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

Health and Safety

THOROSEAL®

Warning!

Thoroseal® contains Portland cement; silica, crystalline quartz; iron oxide; magnesium oxide; limestone; gypsum; calcium hydroxide; calcium oxide and anhydrite.

Risks

Product is alkaline on contact with water and may cause injury to skin or eyes. Ingestion or inhalation of dust may cause irritation. Contains small amount of free respirable quartz which has been listed as a suspected human carcinogen by NTP and IARC. Repeated or prolonged overexposure to free respirable quartz may cause silicosis or other serious and delayed lung injury.

Precautions

KEEP OUT OF THE REACH OF CHILDREN. Avoid contact with skin, eyes and clothing. Prevent inhalation of dust. Wash thoroughly after handling. Keep container closed when not in use. DO NOT take internally. Use only with adequate ventilation. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use NIOSH/ MSHA approved respiratory protection in accordance with applicable federal, state and local regulations.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

Refer to Material Safety Data Sheet (MSDS) for further information.

Proposition 65

This product contains material listed by the state of California as known to cause cancer, birth defects, or other reproductive harm.

VOC Content

0 lbs/gal or 0 g/L, less water and exempt solvents.

**For medical emergencies only,
call ChemTrec (1-800-424-9300).**

**BASF Construction Chemicals, LLC –
Building Systems**

889 Valley Park Drive
Shakopee, MN, 55379

www.BuildingSystems.BASF.com

Customer Service 800-433-9517
Technical Service 800-243-6739



LIMITED WARRANTY NOTICE Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, **BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS,** and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all **CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND.** BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

For professional use only. Not for sale to or use by the general public.

Form No. 1019906 9/07

Printed on recycled paper including 10% post-consumer fiber.

© 2007 BASF
Printed in U.S.A.