

TREMproof® 250GC

Single Component, Rapid Curing, Fluid-Applied Elastomeric Waterproofing Membrane

Product Description

TREMproof 250GC is a rapid-curing, high solids, VOC compliant modified polyurethane waterproofing membrane. It can be applied to damp and Green concrete. TREMproof 250GC is a one-part moisture curing elastomer available in three viscosities: Self-Leveling, Roller and Trowel.

Basic Uses

TREMproof 250GC is designed for use on backfilled walls, split slab applications, planters and submerged conditions.

Features and Benefits

TREMproof 250GC can be applied in as little as 24 hours following the removal of concrete forms to keep construction moving. It can also be applied to damp concrete or plywood, reducing the delays associated with rain or other sources of water. The unique ability to catalyze TREMproof 250GC with water when desired will speed cure times, especially cold temperatures and low relative humidity, to further compress the construction schedule. TREMproof 250GC can be applied at a rate of up to 120 mils in a single lift to speed application without sacrificing performance. It can also be applied in multiple lifts to achieve a 215 mil high-build system when maximum protection is required.

Packaging

5 gal. (19L) pails, 36 pails/pallet
55 gal. (208 L) drums, 4 drums/pallet

Coverage Rates

Wet Mil Thickness	Square Ft/Gal	Ltr/ Sq. Meter
215	7.5	5.84
120	13	3.26
90	18	2.45
60	25	1.63

Installation

Refer to TREMproof 250GC Application Instructions for specific application details. The techniques involved may require modification to adjust to job-site conditions. Consult Tremco for specific design requirements.

Availability

Available from your local Tremco Representative, Tremco distributor or warehouse.

Limitations

Not for use in gas vapor conditions. Do not apply to contaminated surfaces. Not to be used as an exposed or wearing surface. Use with adequate ventilation. Concrete forms must be removed a minimum of 24 hours before TREMproof 250GC can be applied. Not approved for direct contact with asphalt-based products. Contact Tremco for compatibility information and job-specific recommendations on tie-in and termination details.

Warranty

Tremco warrants its Membranes to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Membranes. Tremco's sole obligation shall be, at its option, to replace, or refund the purchase of the quantity of Tremco Membrane proved to be defective and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com
for the most up-to-date Product Data Sheets.

TYPICAL PHYSICAL PROPERTIES

ASTM C-836 Standard Specification for High Solids Content,
Cold Liquid-Applied Elastomeric Waterproofing Membrane for use with Separate Wearing Course

Physical Property	Test Method/Requirement	Results
Material	Shall cure and maintain seal against water	Pass
Stability (80 F/26.7 C)	Shelf life 6 months	1 year
Hardness, Shore 00	50 minimum	70-80
Vertical Hold*	60 mils	120+
Weight Loss	20% maximum loss 80% solids minimum	10% Loss 90% Solids
Low Temperature Flexibility and Crack Bridging	Ten Cycles, -15 F/-26 C (0" – 1/8", 1/8" – 0" = 1 cycle; 0 – 3.2 mm, 3.2 mm – 0 = 1 cycle) No cracking	Pass
Adhesion-in Peel after Water Immersion (Unprimed)	1 lbf/in. (4.4 N)	26 lbf/in. (22.2 – 35.6N)
Extensibility After Heat Aging	Membrane must bridge 1/4" (6.4 mm) crack	Pass

* Roller and Trowel Grade only. Self Leveling Grade is not designed to hold on a vertical.



Tremco Commercial Sealants & Waterproofing

3735 Green Road, Beachwood, OH 44122 // Phone: 216.292.5000 // 800.321.7906
220 Wicksteed Avenue, Toronto, ON M4H 1G7 // Phone: 416.421.3300 // 800.363.3213
1451 Jacobson Avenue, Ashland OH 44805 // Phone: 419.289.2050 // 800.321.6357