



NO. 341-B

MasterFormat: 03 05 00

W. R. MEADOWS®

SEALTIGHT®

MAY 2011
(Supersedes July 2006)

HYDRASET-FREE®

Non-Chloride Concrete Set Accelerator

DESCRIPTION

HYDRASET-FREE non-chloride concrete set accelerator is a ready-to-use, liquid admixture. It accelerates initial setting time one to three times faster than normal for mortar and concrete.

HYDRASET-FREE improves workability and strength while it hastens the hydration of cement. It makes the mix easier to place and speeds construction by shortening the initial set and curing time. Labor and time are saved, because forms and other protection can be removed earlier and finishing can be initiated. HYDRASET-FREE should not be limited to use during months when temperatures are in the 20° to 45° F (-7° to 7° C) range. Increased workability and earlier strength are also obtained when temperatures are in the 50° to 65° F (10° to 18° C) range, because any time the temperature drops below 70° F (21° C), there is a reduction in the rate of cement hydration. During cold and hot weather applications, follow ACI 305 & 306 recommendations.

USES

HYDRASET-FREE is recommended for use during cool and cold weather to accelerate the set time and reduce the risk of frozen mortar and concrete mixes. However, HYDRASET-FREE can be used any time you want to accelerate the set time to decrease turnaround time. HYDRASET-FREE will also provide limited protection to reinforcing steel in concrete structures.

FEATURES/BENEFITS

- Accelerates initial set time one to three times faster than normal for concrete and mortar.
- Aids in strength development.
- Speeds up hydration of cement.
- Non-chloride formula.
- Increases workability of concrete or mortar.
- Speeds construction due to reduced setting and curing time.
- Allows earlier removal of concrete forms or other protection.
- Permits earlier finishing.
- VOC compliant.

PACKAGING

5 Gallon (18.93 Liter) Pails
55 Gallon (208.20 Liter) Drums

SPECIFICATIONS

ASTM C 494, Type C
AASHTO M 194, Type C
Corps of Engineers CRD C 87, Type C

CONTINUED ON REVERSE

W. R. MEADOWS, INC.

P.O. Box 338 • HAMPSHIRE, IL 60140-0338
Phone: 847/214-2100 • Fax: 847/683-4544
1-800-342-5976
www.wrmeadows.com

HAMPSHIRE, IL /CARTERSVILLE, GA /YORK, PA
FORT WORTH, TX /BENICIA, CA /POMONA, CA
GOODYEAR, AZ / MILTON, ON /ST. ALBERT, AB

APPLICATION

HYDRASET-FREE is added directly to the mix water. Reduce the amount of water proportionally to compensate for the liquid addition. For masonry mortar, two quarts (1.89 liters) of HYDRASET-FREE for each 94 lb. (42.73 kg) bag of cement should be used. For mortar cements that are 50% Portland cement and 50% lime, one-half the amount, or one quart (950 ml) of HYDRASET-FREE is required.

For concrete, the following quantities are recommended:

<u>TEMPERATURE RANGE</u>	<u>SUGGESTED QUANTITY OF HYDRASET-FREE FOR EACH 94 lb. (42.73 kg) BAG OF CEMENT</u>
Above 70° F (21° C)	1 pt. (.47 L)
70° to 32° F (21° to 0° C)	1 qt. (.95 L)
32° to 25° F (0° to -4° C)	1 to 1 1/2 qt. (.94 to 1.42 L)
25° to 20° F (-4° to -7° C)	2 qt. (1.89 L)

PRECAUTIONS

HYDRASET-FREE affects only the Portland cement portion of the mix and is not an antifreeze for the water portion. Protect from freezing. HYDRASET-FREE has no effect on straight lime mortars and should not be used with oxychloride stuccos. Use HYDRASET-FREE directly from the factory-sealed container; do not dilute. Avoid direct contact. Ingestion may cause moderate to severe irritation of the digestive tract. Read and follow complete application information and precautions on container, prior to use. Consult product Material Safety Data Sheet for complete health and safety information.

LEED INFORMATION

May help contribute to LEED credits:

- IEQ Credit 4.2: Low-Emitting Materials – Paints and Coatings
- IEQ Credit 4.3: Low-Emitting Materials – Flooring Systems
- MR Credit 2: Construction Waste Management
- MR Credit 5: Regional Materials

For most recent data sheet, further LEED information, and MSDS, visit www.wrmeadows.com.



LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.